MAY 3 1 2011

Amendments to the Claims

9894966354

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

- 1. (Currently Amended) A siloxane resin comprising the units:
 - (i) $(R^{1}_{3}SiO_{1/2})_{a}$
 - (ii) $(R^2_2SiO_{2/2})_b$
 - (iii) (R3SiO3/2)c, and
 - (iv) (SiO_{4/2})_d

wherein

R¹, R², and R³ are independently an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group, or an amino group,

a has a value 0.05 to 0.5,

b has a value of zero to 0.3,

c has a value of 0.05 to 0.65 greater than zero,

d has a value of 0.05 to 0.6,

the value of a + b + c + d = 1,

and the siloxane resin has a weight average molecular weight of 26,900 to 25,300,000 and with the proviso that greater than 40 mole % of the R³ groups in the siloxane resin are propyl.

2. (Original) The siloxane resin of claim 1 wherein the siloxane resin is selected from MQ-T propyl resins comprising the units;

 $((CH_3)_3SiO_{1/2})_a$,

 $(R^3SiO_{3/2})_c$, where $R^3 = CH_3CH_2CH_2$, and

 $(SiO_{4/2})_d$

MQ-T propyl resins comprising the units;

 $((CH_3)_3SiO_{1/2})_{B}$

 $((CH_3)_2SiO_{2/2})_b$,

```
(R^3SiO_{3/2})_c, where R^3 = CH_3CH_2CH_2, and
         (SiO<sub>4/2</sub>)<sub>d</sub>
MQ-T propyl resins comprising the units;
         ((CH_3)_3SiO_{1/2})_a,
         ((CH_3)_2SiO_{2/2})_b, ((CH_3)(C_6H_5)SiO_{2/2})_{b'},
        (R^3SiO_{3/2})_c, where R^3 = CH_3CH_2CH_2, and
         (SiO_{4/2})_d
MQ-T propyl resins comprising the units;
         ((CH_3)_3SiO_{1/2})_a,
         ((CH_3)_2SiO_{2/2})_b
        (R^3SiO_{3/2})_c, where R^3 = CH_3CH_2CH_2-, and (C_6H_5SiO_{3/2})_c
         (SiO_{4/2})_d
MQ-T propyl resins comprising the units;
        ((CH_3)_3SiO_{1/2})_a,
        ((CH_3)_2SiO_{2/2})_b, ((CH_3)(C_6H_5)SiO_{2/2})_b,
        (R^3SiO_{3/2})_c, where R^3 = CH_3CH_2CH_2, (C_6H_5SiO_{3/2})_c, and
        (SiO_{4/2})_{d}
```

9894966354

wherein a has a total value in the resin of 0.05 to 0.5, the sum of b + b' has a total value in the resin of zero to 0.3, c has a total value in the resin of 0.05 to 0.65, and d has a total value in the resin of 0.05 to 0.6.

- 3. (Original) A method of making a siloxane resin comprising reacting:
 - A) a MQ resin comprising at least 80 mole % (R¹₃SiO_{1/2})_a and (SiO_{4/2})_d units where R¹ is an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group, or an amino group,

a and d has a value greater than zero, and the ratio of a/d is 0.5 to 1.5;

and

9894966354

- B) a T propyl resin comprising at least 80 mole % R³SiO units, where R3 is an alkyl group having from 1 to 8 carbon atoms, an aryl group, a carbinol group, or an amino group, c has a value greater than zero, and with the provisio that at least 40 mole % of the R³ groups are propyl. wherein the weight ratio of A/B is from 95:5 to 15:85.
- 4. (Canceled)
- 5. (Previously Presented) A personal care product comprising the siloxane resin of claim 1.
- 6. (Original) The personal care product of claim 5, where the personal care product is a cosmetic product.
- 7. (Original) The personal care product of claim 5, where the personal care product is a hair care product.
- 8. (Previously Presented) A personal care product comprising the siloxane resin of claim 2.
- 9. (Previously Presented) The personal care product of claim 8, where the personal care product is a cosmetic product.
- 10. (Previously Presented) The personal care product of claim 8, where the personal care product is a hair care product.